Processing of BRECO®- and BRECOFLEX® timing belts Coating materials. Mechanical rework.

Welded on profiles.











Keeping things moving!

Innovation is what drives us. As the manufacturer of BRECO® and BRECOFLEX® timing belts, BRECO Antriebstechnik Breher GmbH & Co. KG is the world's most innovative producer in the field of polyurethane timing belt technology. Abrasion-resistant polyure thane for belt bodies and high-strength steel cord tension carriers form the basis of a reliable, first-class product.

As a result of years of experience in working with thermoplastic polyurethane, the development of the BRECO® and BRECOFLEX® production processes and their use, the BRECO name has become synonymous with polyurethane timing belts. The results of the decades of experience gained by countless users of the products are reflected in the BRECO® and BRECOFLEX® timing belts, as well as the toothed pulleys optimised for use with the belts and various other components made by BRECO. The consistent use of nothing but high grade raw materials and our intensive coordination with our suppliers to meet the needs of our customers guarantee extremely high quality.

One focal point is the development and production of special belts for a wide range of applications. The large number of belt coatings and diverse flight shapes allow an extremely broad range of uses for BRECO® and BRECOFLEX® timing belts. We offer several belt and tension carrier materials to cater for applications in very cold or very hot environments, for example.

But even for simple applications, BRECO timing belts offer all the advantages and quality expected of a high-end branded product. Safety, durability, accuracy and availability are some of the benefits that ultimately have a positive impact on costs too.

All of our products conform to the European RoHS Directive, which restricts the use of hazardous substances.

Staying safely on the move.



Page

Table of Contents

Coatings for general transport tasks

T version (extruded)
PU 385
HV film
T-groove (TR1 and TR2)
WM 385
NP 385
FG 385
PU 60
Polythane D15
PU yellow
PU grey
Celloflex
Hamid
Linatex HM
RP 430
Correx
Sylomer brown
Sylomer yellow
Sylomer blue
Sylomer green
Sylomer red
Sylomer grey
Sylodyn green
Sylodyn yellow
Supergrip green
Supergrip blue
Minigrip green
Minigrip blue
PVC film blue
Porol
NBR 65

Coatings for transporting food

Linaplus FG FDA	19
PVC herringbone FDA	19
HV film FDA	19
PVC film white FDA	20
PVC dots white FDA	20
Supergrip FDA	20

Coatings with friction-reducing properties

PAZ	1
PAR	1
PAZ-PAR	1

4

Coatings for use at higher contact temperatur
Linatrile TT 60 Viton Chrome leather Linard 60
Coatings with electrically conductive propertie
PA fabric, antistatic
Processing of coatings
Mechanical processing
Processing of timing belts
Milling, drilling, stamping, grinding Water jet cutting
BRECO [®] - and BRECOFLEX [®] timing belts with w
Variety of uses Construction features Selection of standard profiles
BRECO [®] timing belt with high-strength and re
Description
General information
Support rail



5

Page elded on profiles novable profile connection

Coated polyurethane timing belts

Resistance

Depending on the application the resistance of each material part of the coated timing belt is to be viewed separately. The material resistance depends, among others, on the pH value, the concentration, the temperature and the influencing time of the medium. Simple oils generally have no damaging effect on the belt. Additives in the oil and temperatures over approx. 40°C can reduce the longevity.

Friction

The friction of the belt on a support produces heat. This increases the more the belt is loaded by the items to be transported. The bed support must be selected such that the friction value of the transport belt in contact with the material of the bed plate results in a minimum value. The bed plate should guarantee good heat dissipation under high pressure forces.

The friction value changes temperature dependent. It increases as the temperature rises and reduces at temperatures below zero (frost).

Information

You should ask for advice for coatings over 75 mm wide and approx. 2 mm thick because of the different processing properties.

Drives with counter-bending

Coated timing belts are generally suitable for drives with counter-bending. For this, very soft coatings (e.g. Sylomer) should be set up with reduced pretensioning.

Coatings that are manufactured based on natural rubber, such as Linatex, can be used for counter-bending (back pulleys) only to a limited extent. Please consult our technical advice service for this.

Temperature effect / synchronising pulley diameter

When transporting hot goods (above approx. 80°C) it must be ensured that the duration of contact is as short as possible, to avoid heating the belt's substructure to over 80°C. Over a short distance, or for a short time, a coated belt can withstand higher thermal stress, as long as sufficient cooling is provided in the remaining revolution period.

In the temperature range from approx. 60°C the tooth shear strength reduces slightly. An additional safety measure is only needed if the teeth are subjected to major stress.

7

At low ambient temperatures, the flexibility of the coating reduces. Larger diameters for the synchronised pulleys should therefore be selected than at normal temperatures (see diagram). The flexibility of the timing belt also reduces at low temperatures.

The minimum diameters serve as a guideline. They apply at an ambient temperature of 20°C and speed of 1 m/s, and assuming a low burden from the transported goods. If the exact usage details are known, it is possible to reduce the diameters. Our sales partners will be happy to help you.

The minimum pulley diameters stated in the following tables for the different coatings apply for homogenously applied coatings with an even thickness. Interruptions in the coating, e.g. due to cuts or grooves, cause significant notch effects and require considerably higher minimum diameters. Our sales partner can advise you on this issue.



Coated polyurethane timing belts

BRECO® and BRECOFLEX® timing belts consist of wear resistant polyurethane (PUR) and high tensile steel cord tension members. The coating of the timing belts with various materials provides a variety of application possibilities in the transport technology.

The selection of the correct coating depends on the transport item properties and the required grip. High friction for a good carrying effect, low friction to reduce the power transmission performance, soft for sensitive items or hard for sharpedged items are the determining factors.

Every material involved assumes its task according to its specific property.

To meet specific transport applications, the tooth side and/or the transport side can be mechanically reworked. In this manner, the flexibility of the entire belt can be restored by making incisions in thick coatings.

6



Synchronising pulley diameter



(glass, wood, metal, paper, textiles, cardboard packaging, wet area)

Properties			
Colour	transparent		
Standard thickness [mm]	1,5 (5 mm pitch) 2 (Pitch 10, 15, 20, inch pitch)		
Min. pulley diameter [mm]	80 80		
Material / Hardness	polyurethane/approx. 85 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm (grinded ±0,1 mm possible)		
Temperature resistance	-20°C to +80°C		
Chemical resistance	resistant to simple oils and grease, petrol, ozone		
Processing	contours can be grinded and milled and surface grinded		



Properties				
Colour	transparent			
Standard thickness [mm]	3	4	5	6
Min. pulley diameter [mm]	80	120	150	180
Material / Hardness	polyurethane/approx. 85 Shore A			
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm (grinded ±0,1 mm possible)			
Temperature resistance	-20°C to +80°C			
Chemical resistance	resistant to simple oils and grease, petrol, ozone			
Processing	contours can be grinded and milled and surface grinded			



Properties			
Colour	transparent glossy		
Standard thickness [mm]	1 2		
Min. pulley diameter [mm]	60	80	
Material / Hardness	polyurethane/approx. 85 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm (grinded ±0,1 mm possible)		
Temperature resistance	-20°C to +80°C		
Chemical resistance	resistant to simple oils and grease		
Processing	contours can be grinded and milled		

Properties			
Colour	transparent		
Standard thickness [mm]	TR1: 2,4 TR2: 2,5 Groove depth: 0,5 Groove depth: 1,		
Min. pulley diameter [mm]	80	80	
Material / Hardness	polyurethane/approx. 85 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,5 mm		
Temperature resistance	-20°C to +80°C		
Chemical resistance	resistant to simple oils and grease, petrol, ozone		
Processing	-		

Properties		
Colour	transparent	
Standard thickness [mm]	4	
Min. pulley diameter [mm]	120	
Material / Hardness	polyurethane/approx. 85 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm	
Temperature resistance	-20°C to +80°C	
Chemical resistancet	resistant to simple oils and grease, petrol, ozone	
Processing	-	

Properties		
Colour	transparent	
Standard thickness [mm]	4	
Min. pulley diameter [mm]	120	
Material / Hardness	polyurethane/approx. 85 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,4 mm	
Temperature resistance	-20°C to +80°C	
Chemical resistance	resistant to simple oils and grease, petrol, ozone	
Processing	-	















(glass, wo	od, metal,	paper,	textiles
cardboard	packaging	, wet a	area)

Properties	
Colour	transparent
Standard thickness [mm]	4
Min. pulley diameter [mm]	120
Material / Hardness	polyurethane/approx. 85 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ±0,4 mm
Temperature resistance	-20°C to +80°C
Chemical resistance	resistant to simple oils and grease, petrol, ozone
Processing	-
Note	the symmetrical position of the coating profile on the belt is not ensured. If this is required, please specify when ordering

Properties					
Colour		tı	ransparer	nt	
Standard thickness [mm]	2	3	4	5	6
Min. pulley diameter [mm]	80	80	120	150	180
Material / Hardness	pol	yurethan	e/approx	. 60 Shor	e A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm (grinded ±0,1 mm possible)				
Temperature resistance	-20°C to +80°C				
Chemical resistance	resistant to simple oils and grease, petrol, ozone				
Processing	contou	ırs can be sur	e grinded face grin	and mill ded	ed and
Special feature		high v	wear resis	stance	

Properties						
Colour	yellowish-transparent, other colours upon request					
Standard thickness [mm]	2	2 3 4 5				
Min. pulley diameter [mm]	60	80	80	100	100	
Material / Hardness	polyurethane/approx. 70 Shore A					
Tolerances	tolerance for total thickness (timing belt + coating) ±0,6 mm (grinded ±0,1 mm possible)					
Temperature resistance	-20°C to +80°C					
Chemical resistance	resistant to simple oils and greases, good resistance to ozone, UV radiation					
Processing	contou	irs can be sur	grinded face grine	and mill ded	ed and	

10

Properties							
Colour				yellow			
Standard thickness [mm]	2	3	4	5	6	8	10
Min. pulley diameter [mm]	70	70	90	110	110	110	130
Material / Hardness	F	olyure	ethane	/appro	x. 55 S	Shore A	4
Tolerances	tolerance for total thickness (timing belt + coating) ± 0,4 mm (grinded ±0,1 mm possible)						
Temperature resistance	-10°C to +70°C						
Chemical resistance	resistant to simple oils and grease, petrol, ozone						
Processing	cont	ours c	an be surfa	grinde ace grii	d and nded	milled	and
Other areas of use			sola	ar indu	stry		

Properties							
Colour	grey						
Standard thickness [mm]	2	3	4	5	6	8	10
Min. pulley diameter [mm]	70	70	90	110	110	110	130
Material / Hardness	F	olyure	ethane	/appro	ox. 55 S	Shore A	4
Tolerances	tolei + co	rance f pating)	or tota) ± 0,4 p	al thick mm (g ossible	kness (Irindec e)	timing d ±0,1	belt mm
Temperature resistance	-10°C to +70°C						
Chemical resistance	re	esistan	t to sir not wa	nple o ater-re	ils and sistant	greas	e,
Processing	cont	ours c	an be surfa	grinde ace grii	d and nded	milled	and

Properties								
Colour		yellowish-brown						
Standard thickness [mm]	2 3 4 5 6 8							
Min. pulley diameter [mm]	40	60	60	80	80	100	120	
Material / Hardness	mic	rocellu	ılar ela appro	istome x. 350	r polyı kg/m3	uretha	ne /	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm							
Temperature resistance	-30°C to +80°C							
Chemical resistance	resist	tant to	simpl	e oils a	nd gre	ease, o	zone	
Processing	cont	ours c	an be surfa	grinde ace grii	d and nded	milled	and	





(glass, wood, metal, paper, textiles, cardboard packaging, wet area)

Properties	
Colour	top layer green, bottom layer black
Standard thickness [mm]	1,4
Min. pulley diameter [mm]	20
Material / Hardness	transport side NBR rubber green, middle layer Hamid, bottom layer NBR rubber black
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm
Temperature resistance	-30°C to +60°C
Chemical resistance	resistant to simple oils and grease, water
Processing	-



Properties							
Colour	red						
Standard thickness [mm]	2	3	4	5	6	8	10
Min. pulley diameter [mm]	60	80	80	80	100	100	120
Material / Hardness	95%	natur	al rubb	oer / ap	oprox.	38 Sho	ore A
Tolerances	tolerance for total thickness (timing belt + coating) -1/+1,8 mm (grinded ±0,2 mm possible)						
Temperature resistance	-40°C to +70°C						
Chemical resistance	oil-proof to a limited extent, resistant to wet abrasion, water resistant, avoid exposure to direct sunlight						
Processing	con	itours	can be sor	grinde ne ext	ed and ent	l milleo	d to
Note	fro	om 3 n	nm coa ask	ating t for ad	hickne vice	ss plea	se



Properties						
Colour	yellow					
Standard thickness [mm]	2	3	4	5	6	
Min. pulley diameter [mm]	40	50	50	70	70	
Material / Hardness	natural rubber, approx. 39 Shore A					
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,2 mm possible)					
Temperature resistance	-35°C to +80°C					
Chemical resistance	resi	stant to s	imple oil	s and gre	ease	
Processing	conto son	urs can b ne extent	e grinded and surf	d and mil face grind	led to ded	

12 🦯

Properties						
Colour	light brown					
Standard thickness [mm]	6	10				
Min. pulley diameter [mm]	80 120					
Material / Hardness	para rubber, approx. 36 Shore A					
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,2 mm possible)					
Temperature resistance	up to approx. +70°C					
Chemical resistance	resistant to simp	e oils and grease				
Processing	contours can be grinded and milled to some extent and surface grinded					

Properties						
Colour		light brown				
Standard thickness [mm]	6	6 12 (Other thicknesses upo request)				
Min. pulley diameter [mm]	60	80				
Material / Hardness	mixed cell polyurethane, 400 kg/m ³					
Tolerances	tolera + co	ince for ating) ±	total thickness (timing belt 0,7 mm (grinded ±0,3 mm possible)			
Temperature resistance	-30°C to +70°C					
Chemical resistance	resistant to simple oils and grease					
Processing	contours can be grinded and milled to some extent and surface grinded					

Properties					
Colour	yellow				
Standard thickness [mm]	6	6 12 (Other thicknesses up request)			
Min. pulley diameter [mm]	60	80			
Material / Hardness	mixed cell polyurethane, 150 kg/m ³				
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)				
Temperature resistance	-30°C to +70°C				
Chemical resistance	resistant to simple oils and grease				
Processing	contours can be grinded and milled to some extent and surface grinded				







(glass, wood, metal, paper, textiles, cardboard packaging, wet area)

Properties						
Colour		blue				
Standard thickness [mm]	6	12	(Other thicknesses upon request)			
Min. pulley diameter [mm]	60	80				
Material / Hardness	mixed cell polyurethane, 220 kg/m ³					
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)					
Temperature resistance	-30°C to +70°C					
Chemical resistance	resistant to simple oils and grease					
Processing	contours can be grinded and milled to some extent and surface grinded					



Properties			
Colour	green		
Standard thickness [mm]	6	12	(Other thicknesses upon request)
Min. pulley diameter [mm]	60	80	
Material / Hardness	mixed cell polyurethane, 300 kg/m ³		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)		
Temperature resistance	-30°C to +70°C		
Chemical resistance	resistant to simple oils and grease		
Processing	contours can be grinded and milled to some extent and surface grinded		



Properties			
Colour	red		
Standard thickness [mm]	6	12	(Other thicknesses upon request)
Min. pulley diameter [mm]	80	100	
Material / Hardness	mixed cell polyurethane, 510 kg/m ³		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)		
Temperature resistance	-30°C to +70°C		
Chemical resistance	resistant to simple oils and grease		
Processing	contours can be grinded and milled to some extent and surface grinded		

14

Properties			
Colour	grey		
Standard thickness [mm]	6 12 (Other thicknesses upon request)		
Min. pulley diameter [mm]	80	100	
Material / Hardness	mixed cell polyurethane, 680 kg/m ³		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)		
Temperature resistance	-30°C to +70°C		
Chemical resistance	resistant to simple oils and grease		
Processing	contours can be grinded and milled to some extent and surface grinded		

Properties		
Colour	green	
Standard thickness [mm]	6	
Min. pulley diameter [mm]	100	
Material / Hardness	closed-cell polyurethane, 600 kg/m ³	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)	
Temperature resistance	-30°C to +70°C	
Chemical resistance	resistant to simple oils and grease	
Processing	contours can be grinded and milled to some extent and surface grinded	

Properties	
Colour	yellow
Standard thickness [mm]	6
Min. pulley diameter [mm]	80
Material / Hardness	closed-cell polyurethane, 450 kg/m ³
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm (grinded ±0,3 mm possible)
Temperature resistance	-30°C to +70°C
Chemical resistance	resistant to simple oils and grease
Processing	contours can be grinded and milled to some extent and surface grinded







(glass, wood, metal, paper, textiles, cardboard packaging, wet area)

Properties		
Colour	green	
Standard thickness [mm]	4	
Min. pulley diameter [mm]	60	
Material / Hardness	PVC, approx. 40 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-15°C to +90°C	
Chemical resistance	limited resistance to solvents, oils and greases; resistant to acids and alkalis	
Processing	-	



Properties		
Colour	bluish-green	
Standard thickness [mm]	4	
Min. pulley diameter [mm]	60	
Material / Hardness	PVC, approx. 40 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-15°C to +90°C	
Chemical resistance	limited resistance to solvents, oils and greases; resistant to acids and alkalis	
Processing	-	



Properties		
Colour	green	
Standard thickness [mm]	1,5	
Min. pulley diameter [mm]	30	
Material / Hardness	PVC, approx. 65 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-10°C to +110°C	
Chemical resistance	resistant to oils, greases, acids and alkalis	
Processing	-	

Properties		
Colour	bluish-green	
Standard thickness [mm]	1,5	
Min. pulley diameter [mm]	30	
Material / Hardness	PVC, approx. 50 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-15°C to +90°C	
Chemical resistance	resistant to solvents, oils and greases; resistant to acids and alkalis	
Processing	-	

Properties			
Colour	blue		
Standard thickness [mm]	1 (2 / 3 / 4 / 5 / 6 mm upon request)		
Min. pulley diameter [mm]	30		
Material / Hardness	PVC, approx. 65 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm		
Temperature resistance	-15°C to +90°C		
Chemical resistance	limited resistance to solvents, oils and greases; resistant to acids and alkalis		
Processing		-	
Other areas of use	pharmaceutical industry		

Properties			
Colour	black		
Standard thickness [mm]	3 5 10		
Min. pulley diameter [mm]	40	60	80
Material / Hardness	closed-cell cellular rubber, 160-200 kg/m³		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm		
Temperature resistance	-40°C to +75°C		
Chemical resistance	resistant to water, seawater, methanol, acetone, detergent, acids and alkalis		
Processing	-		



18



Properties			
Colour	black		
Standard thickness [mm]	1,5 3		
Min. pulley diameter [mm]	60	80	
Material / Hardness	nitrile rubber, approx. 60-70 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ±0,6 mm (grinded ±0,2 mm possible)		
Temperature resistance	-35°C to +70°C		
Chemical resistance	resistant to oils, and to some extent acids and alkalis		
Processing	contours can be grinded and milled to some extent and surface grinded		

Properties			
Colour		white	
Standard thickness [mm]	3 5 6		6
Min. pulley diameter [mm]	40	40	40
Material / Hardness	vulcanised nat	ural rubber, app	rox. 38 Shore A
Tolerances	tolerance for total thickness (timing belt + coa- ting) -1/+1,8 mm (grinded ±0,2 mm possible)		
Temperature resistance	-40°C to +70°C		
Chemical resistance	resistant to chemicals; material does not leave pressure marks		
Processing	contours can be grinded and milled and surface grinded		
Note	FDA approval in conformity with the criteria of the FDA Code of Federal Regu- lations, section 177.1680, the European Regulation (EC) 1935-2004, Regulation (EU) no. 10/2011 and European Commissi- on Directives 90/128/EEC and 96/11/EC		

Properties		
Colour	white	
Standard thickness [mm]	3	
Min. pulley diameter [mm]	60	
Material / Hardness	PVC, approx. 65 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-10°C to +110°C	
Chemical resistance	resistant to oils, greases, acids and alkalis	
Processing	-	
Note	FDA approval in conformity with the criteria of the FDA Code of Federal Regu- lations, section 177.1680, the European Regulation (EC) 1935-2004, Regulation (EU) no. 10/2011 and European Commissi- on Directives 90/128/EEC and 96/11/EC	

Properties		
Colour	transparent glossy	
Standard thickness [mm]	1 2	
Min. pulley diameter [mm]	60	80
Material / Hardness	polyurethane/approx. 85 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,4 mm (grinded ±0,1 mm possible)	
Temperature resistance	-20°C to +80°C	
Chemical resistance	resistant to simple oils and grease	
Processing	contours can be grinded and milled	



Coatings with friction-reducing properties

Coatings for transporting food



PVC film white FDA



PVC dots white FDA



Supergrip FDA

Properties		
Colour	white	
Standard thickness [mm]	2	(1 / 3 / 4 / 5 / 6 mm upon request)
Min. pulley diameter [mm]	60	
Material / Hardness	PVC, approx	a. 48 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-10°C to +110°C	
Chemical resistance	resistant to oils, greases, acids and alkalis	
Processing		-
Note	FDA approval in conformity with the crite- ria of the FDA Code of Federal Regulations, section 177.1680, the European Regulations (EC) 1935-2004, (EC) 2023/2006 and (EU) no. 10/2011 and European Commission Direc- tives 90/128/EEC and 96/11/EC	

Properties	
Colour	white
Standard thickness [mm]	1,5
Min. pulley diameter [mm]	60
Material / Hardness	PVC, approx. 60 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm
Temperature resistance	-10°C to +110°C
Chemical resistance	resistant to oils, greases, acids and alkalis
Processing	-
Note	FDA approval in conformity with the criteria of the FDA Code of Federal Regulations, section 177.1680, the European Regulations (EC) 1935-2004, (EC) 2023/2006 and (EU) no. 10/2011 and European Commission Direc- tives 90/128/EEC and 96/11/EC

Properties		
Colour	white	
Standard thickness [mm]	4	
Min. pulley diameter [mm]	60	
Material / Hardness	PVC, approx. 55 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-10°C to +110°C	
Chemical resistance	resistant to oils, greases, acids and alkalis	
Processing	-	
Note	FDA approval in conformity with the crite- ria of the FDA Code of Federal Regulations, section 177.1680, the European Regulations (EC) 1935-2004, (EC) 2023/2006 and (EU) no. 10/2011 and European Commission Direc- tives 90/128/EEC and 96/11/EC	

20 🆌

Properties		
Colour	green	
Standard thickness [mm]	0,5 0,8	
Min. pulley diameter [mm]	15	25
Material / Hardness	polyamid	
Tolerances	± 0,2 mm	
Temperature resistance	-20°C to +50°C	
Chemical resistance	resistant to simple oils and grease	
Processing	-	

Properties		
Colour	green	
Standard thickness [mm]	0,5	0,8
Min. pulley diameter [mm]	15	25
Material / Hardness	polyamid	
Tolerances	± 0,2 mm	
Temperature resistance	-20°C to +50°C	
Chemical resistance	resistant to simple oils and grease	
Processing	-	

Properties		
Colour	green	
Standard thickness [mm]	0,5	0,8
Min. pulley diameter [mm]	15	25
Material / Hardness	polyamid	
Tolerances	±0,2 mm	
Temperature resistance	-20°C to +50°C	
Chemical resistance	resistant to simple oils and grease	
Processing		-

21



Coatings for use at higher contact temperatures



Properties			
Colour	orange		
Standard thickness [mm]	3 5 6		
Min. pulley diameter [mm]	60	60	60
Material / Hardness	Nitrile-based vulcanised material, approx. 55 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) -1/+1,8 mm (grinded ±0,2 mm possible)		
Temperature resistance	-20°C to +110°C		
Chemical resistance	resistant to oils, greases and other chemi- cals; water resistant		
Processing	contours can be grinded and milled and surface grinded		





Properties		
Colour	black	
Standard thickness [mm]	2	
Min. pulley diameter [mm]	120	
Material / Hardness	polyester fleece	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,5 mm	
Temperature resistance	-10°C to +120°C	
Chemical resistance	against simple oils and greases; electro- static properties	
Processing	-	
Areas of use	glass industry, as a conveyor belt in the warm area	

Properties		
Colour	black	
Standard thickness [mm]	2	4
Min. pulley diameter [mm]	80	100
Material / Hardness	synthetic fluoroelastomer, approx. 70-80 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0,6 mm (grinded ±0,2 mm possible)	
Temperature resistance	-10°C to +190°C (up to 275°C for short periods)	
Chemical resistance	very good resistance to oils, greases, hydrocarbons, acids; impermeable to gas and water vapour	
Processing	contours can be grinded and milled to some extent and surface grinded.	
Potential applications	transportation of s board packaging of glass and	ensitive pars, card- g, transportation metal parts

22

Properties					
Colour	grey				
Standard thickness [mm]	2 3				
Min. pulley diameter [mm]	100	120			
Material / Hardness	leather tanned with chromium salts				
Tolerances	tolerance for total thickness (timing belt + coating) ±0,7 mm				
Temperature resistance	-10°C to +120°C				
Chemical resistance	resistant to oils and greases; weather resistant				
Potential applications	transportation of oil and grease soaked parts, transportation of sheet metal and pipes				

Properties				
Colour	red			
Standard thickness [mm]	3	5	6	
Min. pulley diameter [mm]	60	60	60	
Material / Hardness	silica-reinforced natural rubber, approx. 60 Shore A			
Tolerances	tolerance for total thickness (timing belt + coating) -1/+1,8 mm (grinded ±0,2 mm possible)			
Temperature resistance	-20°C to +110°C resistant to simple oils and greases; very high rebound elasticity contours can be grinded and milled and surface grinded			
Chemical resistance				
Processing				

Properties	
Colour	black
Standard thickness [mm]	0,6
Min. pulley diameter [mm]	20
Material / Hardness	approx. 0,5 mm PU 385, top layer 0,1 mm antistatic fabric
Tolerances	tolerance for total thickness (timing belt + coating) ±0,4 mm
Conductance	10⁵ ohm when new
Potential applications	accumulation conveyors for electrical components

23

Coatings for use at higher contact temperatures





Mechanical processing

24

Coated BRECO® and BRECOFLEX® timing belts can be me-chanically processed for special functional characteristics, depending on the properties of the coating.

Transport belts with thick coatings are less flexible. Their use therefore requires a larger diameter of toothed pulley. Transverse slits or grooves can increase the flexibility of the coating. Where technically possible from a production perspective, milled grooves are used for secure handling and better positioning of products.

Perforated BRECO[®] timing belts are used in vacuum transport systems. BRECOFLEX® timing belts are also available for this purpose. The preferred version of BRECO® timing belts is manufactured with tension carrier-free zones. The teeth are milled lengthways according to the hole size.

In mechanical processing, the larger dimensional tolerances that occur due to material elasticities should be noted. Increased tension can occur in the fibres on the edge of the coatings as a result of mechanical processing when revolving around the toothed pulleys, which may require the use of larger toothed pulley diameters. Please consult our technical advice service for this.

Milling, drilling, stamping, grinding









BRECO® and BRECOFLEX® timing belts can be mechanically processed for special functional characteristics. Timing belts with thick backs that offer a broad range of possibilities for design engineers are available especially for mechanical processing.

Please note that timing belts with thicker backs are less flexible and require toothed pulleys with larger diameters. Better flexibility is achieved through transverse grooves or slits.



Back cross milling

Cross grooves on the belt back enhance the flexibility of the belt. Milled grooves are, in as much as they are possible from the technical feasibility point of view, used to improve safe loading and secure positioning of the products on the belts.





Back longitudinal milling

Back longitudinal milling

Independent on the belt pitch, the belt back shaping offers a wide range of design variants for customised solutions. In this manner, belt guiding can be achieved by a trapezoidal back profile, or a round section supported and moved by means of a prism shaped cross section. Dimensions are to be indicated as depth measure x in relation to the belt back.



Removing individual teeth



Back grinding

26

The backs of all BRECOFLEX® timing belts are ground as standard. For reasons of precision or in order to obtain a roughened surface, all other timing belts of the BRECO delivery range can be ground.



Perforated timing belts

27

Grinding belt edges

Narrower tolerances in the belt width can be achieved by grinding the belt edges. The edges may need to be grinded especially for BRECO[®] timing belts guided by rails. The narrower standard tolerance is ± 0.3 mm. Further narrowing is possible. Please ask for technical advice in this regard.

Removing individual teeth

The removal of individual teeth or entire groups of teeth is possible and should be done for accurate interlinking purposes, for example if the remaining teeth are used to accept the transported goods in a specific position.

Milling teeth lengthwise

BRECO[®] timing belts with tooth profiles milled lengthwise are often used in combination with tension carrier-free zones in vacuum transport systems. BRECO[®] timing belts offer a wide range of products for use in this area. The processing depth x is measured starting from the tip of the tooth and generally ending at the bottom of the space.

Perforated timing belts

The use of perforated BRECO® and BRECOFLEX® timing belts is preferred for areas without tension members (to a limited degree also available as BRECOFLEX® timing belts) and areas with teeth removed in the longitudinal direction, if they are to be employed as suction belts in the vacuum transport technology. The multitude of design possibilities of BRECO® timing belts as vacuum timing belts as well as our extensive experience especially in this field includes the transport of delicate films up to sheet bars of several square meters in size.

Water jet cutting



Water jet cutting

- Precise
- Fast •
- Clean
- Variety of uses
- Environmentally friendly

In addition to milling, drilling, stamping and grinding, BRECO[®] and BRECOFLEX[®] timing belts can also be processed with a water jet cutting machine. Water jet cutting offers a wide range of possibilities. A variety of cut-out contours can be realised with high precision for special purposes. The process is also suitable for cutting flight shapes from pre-process is also suitable for cutting flight shapes from preassembled polyurethane plates of different thicknesses.

Benefits

- Precise cutting edges
- High cutting accuracy •
- Very low heat generation and no warping
- No burrs
- Hardly any post-processing required ٠





28



Possible uses

- Cut-outs (round, oval, triangular, rectangular, etc.) Cut-outs with rounded parts and straight edges Special cuts for splicing Contour cutting of flight shapes •
- ٠
- ٠
- ٠



Variety of uses

Whichever transport purpose BRECO[®] and BRECOFLEX[®] timing belts are used for, the back of the belt can be fitted with any number and sequence of welded-on profiles.

The profiles consist of polyurethane, the same high-quality material as the timing belts themselves. A selection of profile shapes with standard dimensions is shown in this catalogue.

Other customer-specific profile shapes are also available. Within our production capabilities, the profile shape for transported goods and transportation purposes can be freely determined according to the customer's requirements. The injection moulds are manufactured in our own tool building facilities. This ensures fast availability.

Please observe the design guidelines on the following pages.

BRECO[®]- and BRECOFLEX[®] timing belts with welded on profiles





Supply belt



Construction features

At first, the basis for the selection of belt type, belt length and the depending pulleys is the surrounding construction. All belt types of our manufacturing range can be equipped with flights/profiles. Timing belts together with bed plates enable a reduced friction transportation. BRECO® and BRECOFLEX® timing belts in the version PAZ are alternatively available.

Profile selection

The material to be transported and the transport purpose influence the selection of the flight. Following possibilities of flight versions are available:

- Profiles of existing standard tools Profiles are manufactured as polyurethane moulded part Over 2500 standard profiles are available. Depending on their dimensions, standard profiles can be reworked by mechanical processes (drilling, milling). If necessary, explain design requirements by means of a drawing.
- Profiles of sheet material Depending on the quantity, flights will possibly be cut from pre-fabricated PUR sheets. The following board thicknesses are available: 1,5; 2; 3; 4; 5; 6; 7; 8; 10; 11; 15; 20 mm
- Profiles of new tool

Within the framework of our production possibilities, there are practically no limitations for new design requirements as far as the shape of injection moulded flights are concerned. Costs for tools and moulds might apply.

Profile position opposite tooth

The belt flexibility of timing belts is located mainly in the tooth gap area. To retain the timing belt flexibility around the pulley, the profile position "opposite the tooth" is to be preferred.



Profile pitch Tooth pitch

We recommend to select a Profile pitch which is an integral multiple of that of the tooth. Profile pitches other than the integral multiple of the tooth pitch can be supplied, it has, however, to be noted, that a uniform offset of the profile position in relation to the tooth position will accumulate.

Tolerances

The reached profile position of each individual profile is ± 0.5 mm of the intended set point position. A tolerance of ± 0.5 mm is to be taken into account for the profile height.

32

Ordering example:

Construction features



The equipping of the timing belt with profiles is always made as a multiple of the tooth pitch, i.e. the welded on flight position follows exactly the belt tooth pitch. For this reason, a cumulative error from profile pitch to tooth pitch will not occur.

For the required timing belt with profiles the order should preferably be accompanied by a dimensional drawing. The timing belt with profiles can also be defined and transmitted by the order text.

BRECO® timing belt 50 T 10/5000 V-PAZ with welded-on profiles Example: Profile no. 2.3.2.015.008, Number of profiles 100. Profile pitch 50, Profile position opposite the tooth.

Joined version

Joining is made by welding the full profile fitting surface on the back of the belt.

Flash

A flash builds up between flight and back of the belt. A polyurethane overhang with a 0.5 to 1 mm radius could form. Should the flash impair the intended function, ask for "flash removed" in your order information.



timing belts with welded on profiles

Construction features

Profile thickness s

The timing belt flexibility can be influenced by the welded-on flight. Note as a rule that the flight thickness s is to be selected as thin as possible. The table below shows the individually recommended maximum profile thickness s in mm in relation to the selected number of pulley teeth.



Max. thickness s [mm]

	Max. profile thickness in mm when welded on position is opposite tooth													
Type /	Max. profile thickness in mm when welded on position is opposite tooth gap													
pitch	Number of pulley teeth													
	20 25		5	30		40		50		60		100		
T2,5	2,5	1,5	3	1,5	3	2	4	2	4,5	3	5	4	6	6
T5	5	2	6	2	6	3	8	4	9	6	10	8	12	10
T10	8	3	9	4	10	4	12	6	14	9	15	12	20	20
T20	12	5	13	5	15	6	18	8	20	12	23	20	30	30
AT3	3	1,5	4	1,5	4	2	5	3	6	4	6,5	5	8	7
AT5	5	2	6	2	6	3	8	4	9	6	10	8	12	10
AT10	8	3	9	4	10	4	12	6	14	9	15	12	20	20
AT20	12	5	13	5	15	6	18	8	20	12	23	20	30	30
MXL	2	1	2,5	1	2,5	1,5	3,5	1,5	4	2	4,5	3	5	5
XL	5	2	6	2	6	3	8	4	9	6	10	8	12	10
L	6	3	7	3	8	4	10	5	12	7	13	10	16	16
Н	8	4	9	5	10	6	12	7	14	10	15	12	20	20
XH	13	5	14	5	15	6	18	8	20	12	23	20	30	30

Example for the calculation of the profile thickness s for a BRECO® timing belt with pitch T10, which is running around a pulley with 20 teeth:

- When the profile position is "opposite the tooth", profile thickness $s \le 8$ mm,
- When the profile position is "opposite the tooth gap", profile thickness $s \le 3$ mm.

Remark:

We recommend to select the next smaller size as profile thickness when there are intermediate sizes (e.g. 22 teeth).

34

Construction features

Profiles with undercut

The timing belt flexibility is assured, when there are planned corresponding undercuts.



Profile pair

Profile pairs (profile chambers, profile pockets) are preferred in the transport technology for parts positioning and for so-called inset procedures. For the clearance between the profiles, the production tolerance amounts to ± 0.5 mm. Indicate a tolerance reduced to ± 0.2 mm separately, while taking make-ready and/or tool costs into consideration.



Selection of standard profiles

These profiles for welding on only represent a small selection from our entire range. Over 2700 existing profile shapes are available. These profile shapes can be adapted to special requirements by mechanical processing in smaller series.

Our sales partners will gladly help you find solutions for certain transport tasks.





Profile no. 2.3.4.012.024



Construction features

Profiles with moulded inserts

Profiles with moulded inserts can be manufactured for special functional characteristics. To shape moulded inserts (steel, aluminium or similar) please ensure the existence of appropriate undercuts.

Remark: The orderer has to make available a sufficient number of moulded-in inserts with an approx. 5 % surplus for the manufacture of samples.



Profiles with bore holes

It is possible to ask for boreholes for special profile attachments. Tolerances are to be considered.



BRECO[®]- and BRECOFLEX[®]-timing belts with welded on profiles

BRECO[®]- and BRECOFLEX[®]-timing belts with welded on profiles

Selection of standard profiles



38





39

Suitable screw types for brass insert troughs

Allen screws according to DIN 7984 (galvanised) with hexagona size 500 units)

Belt type	Screw type	Screw length	D	н
ATN10 / AT10	M4×8	8 mm	7,0	2,8
	M4×12	12 mm	7,0	2,8
	M4×16	16 mm	7,0	2,8
ATN20 / AT20	M5×12	12 mm	8,5	3,5
	M5×16	16 mm	8,5	3,5
	M5×20	20 mm	8,5	3,5

Suitable screw types for VA insert troughs

Allen screws according to DIN 7984 (VA, material number 1.4301) with hexagonal socket and low head (batch size 500 units)

Belt type	Screw type	Screw length	D	н
ATN10 / AT10	M4×8	8 mm	7,0	2,8
	M4×12	12 mm	7,0	2,8
	M4×16	16 mm	7,0	2,8
ATN20 / AT20	M5×12	12 mm	8,5	3,5
	M5×16	16 mm	8,5	3,5
	M5×20	20 mm	8,5	3,5

Ordering information

The current order designation for the belt types is to be used when ordering. The pitch distances of the belt teeth to be processed must be specified. The insert troughs are available in brass (MS) and stainless steel (VA). Please also use the order designation given here. The screws to be used correspond to the types offered for the ATN system.

Examples:

BRECO® TIMING BELT 75 ATN20 / 5600 V Transverse milling insert trough ATN/AT20, Pitch distance 80 mm Insert trough 75 ATN/AT20 MS, number of units 70 Specification of screw type according to table (optional)

BRECOFLEX® TIMING BELT 50 AT10 / 6800 TPUFD1 Transverse milling insert trough ATN/AT10, Pitch distance 200 mm Insert trough 50 ATN/AT10 VA, number of units 34 Specification of screw type according to table (optional)

A system with many possibilities

The high-strength and removable profile attachment is based on the ATN system. The profiles are attached using screws in inset troughs, which can be used in the tooth by means of subsequent milling of individual belt teeth. The load on the connection is therefore not distributed to the individual inserts like in the ATN system, but rather across the entire width of the tooth. With this type of connection, the range of uses for ATN timing belts extends to areas that previously could not be realised due to an increased burden on the profile.

Another advantage of this connection is the ability to apply the ATN principle to other types of timing belts. Type AT10 and AT20 BRECOFLEX® and BRECO® timing belts can therefore be fitted with screwed on profiles after appropriate processing, so even these "traditional" conveyor belts can virtually achieve the flexibility of the ATN system.





Available insert trough Number of threads widths 32 (only available in VA) 2 2 3



Insert trough ATN/AT10 VA / insert trough ATN/AT20 VA (The insert troughs are (in some cases) also available in brass).

High-strength and removable profile connection







Timing belt guided by support rails

BRECO[®] and BRECOFLEX[®] timing belts have excelled in their use for transportation in many different areas. The belt material polyurethane has beneficial properties with regard to wear and abrasion. This is particularly beneficial when support rails are used (maximum belt speed 1 m/s). Support rails prevent the timing belt run from shifting from the burden of the transported goods.

Support rails can be used with or without lateral guides. Support rails without lateral guides are preferable when no great lateral forces act on the conveyor belt. If lateral forces occur, support rails with lateral guides should be used.

To prevent abrasion, the timing belt must run through the middle of these lateral guides. It is therefore essential that the support rails are set up accordingly with infeed chamfers.

The following applies to the widths B' and b:

- B': There must be a minimum clearance of 0.5 mm between the maximum dimension b and the minimum dimension B'.
- b: Depending on the required accuracy, the tolerance of the belt width can be reduced.

Material

We recommend using a low-friction and abrasion-resistant material such as low-pressure polyethylene. The sliding friction value between standard polyurethane and low-pressure polyethylene is between $\mu \approx 0.3$ and $\mu \approx 0.8$, depending on the material specification of the polyethylene used. We recommend always checking that the material is suitable for the intended use with the supplier of the low-pressure polyethylene.

Other possible combinations:

- Steel with bright surface, sanded if necessary, and polyurethane timing belt with polyamide coating (PAZ/ PAR): μ≈0.2
- Surface-hardened bright aluminium and polyurethane timing belt with polyamide coating (PAZ/PAR): $\mu \approx 0.2 \dots 0.3$



Example of assembly line



Guiding on support rails

42



Distribution partner

Distribution partner

44

			\rightarrow \rightarrow
Anton Klocke Antriebstechnik GmbH Senner Straße 151 D-33659 Bielefeld phone: +49 521 950 05-01 fax: +49 521 950 05-11 www.klocke-antrieb.de info@klocke-antrieb.de	REIFF Technische Produkte GmbH Tübinger Straße 2-6 D-72762 Reutlingen phone: +49 712 132 3-0 fax: +49 712 132 3-318 www.reiff-tp.de zahnriemen@reiff-gmbh.de	Wilhelm Herm. Müller GmbH & Co. KG Heinrich-Nordhoff-Ring 14 D-30826 Garbsen phone: +49 513 145 22-0 fax: +49 513 145 22-110 www.whm.net info@whm.net	W. H. MÜLLER s.r.o. Wilhelm Herm. Mü Pražákova 39 Polska Sp. z o.o. CZ-61900 Brno Polska Sp. z o.o. phone: +420 543 211 008 PL-85-862 Bydgosza phone: +420 543 212 343 phone: +48 523 49 fax: +420 541 217 468 www.whm.cz whm@whm.cz www.whm.pl
Klocke Germany	Sterk in Service Traductor Products	WEIRELM MERKE MILLER 🛞 Germany	WM.MULLER () Czech Republic
Walter Rothermundt GmbH & Co. KG Am Tannenbaum 2 D-41066 Mönchengladbach phone: +49 216 169 462-0 fax: +49 216 166 446 9 www.rothermundt.de info@rothermundt.de	Roth GmbH & Co. KG Andernacher Straße 14 D-90411 Nürnberg phone: +49 911 995 21-0 fax: +49 911 995 21-70 www.roth-ing.de info@roth-ing.de	Aratron AB Smidesvägen 4-8 SE-17141 Solna phone: +46 840 416 00 fax: +46 898 428 1 www.aratron.se info@aratron.se	ARATRON AS Postboks 214 Holmlia N-1204 Oslo phone: +47 231 916 60 fax: +47 231 916 61 www.aratron.no firmapost@aratron.no Movetec Oy Hannuksentie 1 FIN-02270 Espoo phone: +35 895 25 fax: +35 895 25 www.movetec.fi info@movetec.fi
ROTHERMUNDT	roth Germany	Aratron. Sweden	Aratron AS Norway MOVETEC
Hilger u. Kern GmbH Antriebstechnik Käfertaler Straße 253 D-68167 Mannheim phone: +49 621 370 5-0 fax: +49 621 370 5-403 www.hilger-kern.com antriebstechnik@hilger-kern.de	Haberkorn GmbH Modecenterstraße 7 A-1030 Wien phone: +43 174 074-0 fax: +43 174 074-99 www.haberkorn.com info.wien@haberkorn.com	Dinámica Distribuciones S.A. Ctra. No. II, km 592,6 E-08740 S. Andreu de la Barca phone: +34 936 533 500 fax: +34 936 533 508 www.dinamica.net dinamica@dinamica.net	BRECOflex Co., L.L.C. 222 Industrial Way West USA-Eatontown, NJ 07724 phone: +1 732 460-9 500 fax: +1 732 542-6 725 www.brecoflex.com info@brecoflex.com
Higher & Kern Annulation Germany	HABERKORN Austria	DiNAMica Spain	BRECO Nex CL.LLC. USA
THE POWER OF A WELL-MESHED GROUP	Binder Magnetic 1, Allee des Barbanniers F-92632 Gennevilliers-Cedex phone: +33 146 138 080 fax: +33 146 138 099 www.binder-magnetic.com info@binder-magnetic.fr	Transmission Developments Co. (G.B.) LTD Dawkins Road, Hamworthy GB-Poole Dorset BH15 4HF phone: +44 120 267 555 5 fax: +44 120 267 746 6 www.transdev.co.uk sales@transdev.co.uk	BRECO insists on high quality not only in its manufacturing pro everything to do with polyurethane timing belt technology. O themselves offer fi rst-class customer service. BRECO is a member of Mulco Europe EWIV, a European Econo are considered pioneers in the fi eld of polyurethane timing be and the intensive cooperation have been and will continue to mechanical engineering in general.
Distribution partner	France / Belgium	Great Britain	BRECO [®] and BRECOFLEX [®] timing belts - staying safely o

45





ocesses but also in the standard of its advice and service in our distribution partners are all specialists in this fi eld who

mic Interest Grouping (EEIG). All the members of this group elt technology. The trust which has evolved over many years be the basis for innovative power transmission solutions in

on the move.

Available product catalogues - for every application the right product

BRECO® and **BRECOFLEX®** timing belts

- General information (application and calculation notes)
- Endless timing belts (BRECOFLEX®)
- Open length timing belts (BRECO[®] M)
- Endless joined timing belts (BRECO® V)
- Timing belt lock for AT10, T10

ATN-System - BRECO[®] timing belts for transport technology

- General information about the ATN system (application information and notes on calculations)

46

- ATN timing belts
- ATN timing belt lock
- ATN standard profile connection
- ATN profiles
- ATN components

BRECO® and BRECOFLEX® flat belts

- General information
- Endless flat belts (BRECOFLEX®)
- Open length timing belts (BRECO[®] M)
- Open length flat belts (BRECO[®] M)
- Endless joined flat belts (BRECO[®] V)
- Fastening elements

Finishing of timing belts

- Coatings for polyurethane timing belts
- Mechanical rework of coatings
- Mechanical rework of timing belts
- High strength profile connection
- Welded-on profiles

Components

- General information
- Timing pulleys
- Synchronising shafts
- Synchronising pulleys with tensioners
- Tension rollers
- BRECO® fix-clamping elements

BRECObasic®-timing belts

- Product range
- Coatings for BRECObasic® timing belts

BRECOprotect®-timing belts

- Product range

Further information about:

- Sales partners
- New products and developments
- Available catalogues can be found at www.breco.de

Warranty

All information has been compiled with the utmost care and attention and reflects the current state of knowledge. However, we would like to particularly draw your attention to the fact that all technical data is guoted subject to tolerances and must not be interpreted as a guaranteed delivery specifi cation. We reserve the right to make technical changes as part of our continuous product development process.



BRECO® and BRECOFLEX® are registered trademarks of BRECO Antriebstechnik Breher GmbH & Co. KG.

© 2013 BRECO Antriebstechnik Breher GmbH & Co. KG

All rights withheld. No parts of this catalogue may be reproduced. Printed in Germany, engl. version 18/2013/1860

47



